

SID

Factory: Rot am See

Article:

627

ML4

Provided:

Stockburger, Olesja

Customer:

Date:

19.01.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	342		
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		
C-RS-FR4-DS-0.93mm-070+070-TG150-HF	50200935	70	L2	
		930		
		70	L3	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	342		
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	

Thickness after Pressing

B00:

1890 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2090 µm

Dmin:

1690 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

2000 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2200 µm

Dmin:

1800 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

1894 µm

Version 1.2.14.15

© Würth Elektronik