

SID

Factory: Rot am See

Article:

623

ML4

Provided:

Stockburger, Olesja

Customer:

Date:

19.01.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
---------------	----------	----	---------	------------------

A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	1	A00 B00
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	295		2	
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		3	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		4	
C-RS-FR4-ML-0.51mm-105+105-TG150-HF	50200884	105	L2	5	
		510			
		105	L3		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	295		6	
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		7	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		8	
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	9	

Thickness after Pressing

B00:

1440 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1595 µm

Dmin:

1285 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

1550 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1705 µm

Dmin:

1395 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

1450 µm

Version 1.2.14.15

© Würth Elektronik