

SID

Factory: Rot am See

Article:

674

ML8

Provided:

Stockburger, Olesja

Customer:

Date:

25.01.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	1
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	267		2
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		3
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		4
C-RS-FR4-ML-0.10mm-070+070-TG150-HF	50200773	70	L2	5
		100		
		70	L3	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	230		6
		0		7
		0		8
C-RS-FR4-ML-0.10mm-070+070-TG150-HF	50200773	70	L4	9
		100		
		70	L5	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	230		10
		0		11
		0		12
C-RS-FR4-ML-0.10mm-070+070-TG150-HF	50200773	70	L6	13
		100		
		70	L7	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	267		14
		0		15
		0		16
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	17

Thickness after Pressing

B00:

1890 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2090 µm

Dmin:

1690 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

2000 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2200 µm

Dmin:

1800 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

1854 µm

Version 1.2.14.15

© Würth Elektronik