

SID

Factory: Rot am See

Article:

687

ML8

Provided:

Stockburger, Olesja

Customer:

Date:

26.01.2016



Processtechnology: B: Undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	1
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	325		2
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		3
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		4
C-RS-FR4-ML-0.41mm-105+105-TG150-HF	50201189	105	L2	5
		410		
		105	L3	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	230		6
		0		7
		0		8
C-RS-FR4-ML-0.41mm-105+105-TG150-HF	50201189	105	L4	9
		410		
		105	L5	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	230		10
		0		11
		0		12
C-RS-FR4-ML-0.41mm-105+105-TG150-HF	50201189	105	L6	13
		410		
		105	L7	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	325		14
		0		15
		0		16
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	17

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

3110 µm

Version 1.2.14.15

© Würth Elektronik