

# SID

Werk: Rot am See

Artikel:

707

ML12

Erstellt:

Stockburger, Olesja

Kunde:

Datum:

03.02.2016



Prozesstechnik: B: undefiniert

| Materialtext                        | Mat. Nr. | µm  | Aufbau | Prozessaufbau |
|-------------------------------------|----------|-----|--------|---------------|
| A-RS Kupferfolie-018my 330x490mm    | 50200238 | 18  | VS     | 1             |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 210 |        | 2             |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 0   |        | 3             |
|                                     |          | 35  | L2     |               |
| A-RS-FR4-ML-0.30mm-035+035-TG150-HF | 50200655 | 300 |        | 4             |
|                                     |          | 35  | L3     |               |
|                                     |          |     |        | A01           |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 195 |        | 5             |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 0   |        | 6             |
|                                     |          | 35  | L4     |               |
| A-RS-FR4-ML-0.30mm-035+035-TG150-HF | 50200655 | 300 |        | 7             |
|                                     |          | 35  | L5     |               |
|                                     |          |     |        | A02           |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 195 |        | 8             |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 0   |        | 9             |
|                                     |          | 35  | L6     |               |
| A-RS-FR4-ML-0.30mm-035+035-TG150-HF | 50200655 | 300 |        | 10            |
|                                     |          | 35  | L7     |               |
|                                     |          |     |        | A03           |
|                                     |          |     |        | B00           |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 195 |        | 11            |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 0   |        | 12            |
|                                     |          | 35  | L8     |               |
| A-RS-FR4-ML-0.30mm-035+035-TG150-HF | 50200655 | 300 |        | 13            |
|                                     |          | 35  | L9     |               |
|                                     |          |     |        | A04           |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 195 |        | 14            |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 0   |        | 15            |
|                                     |          | 35  | L10    |               |
| A-RS-FR4-ML-0.30mm-035+035-TG150-HF | 50200655 | 300 |        | 16            |
|                                     |          | 35  | L11    |               |
|                                     |          |     |        | A05           |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 210 |        | 17            |
| A-RS-FR4-Prepreg-2116-TG150-HF      | 50200642 | 0   |        | 18            |
| A-RS Kupferfolie-018my 330x490mm    | 50200238 | 18  | RS     | 19            |

Dicke nach Verpressen

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Gesamtdicke über alles

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Kundenforderung

Dicke (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Messstelle: (05) über LM und galv.Cu; beidseitig

nominal:

3086 µm

Version 1.2.14.15

© Würth Elektronik